

POLYCARBONATE FILMS

Properties of JS1501P Series for White Films

EXIM White PC Films, both Standard and Antistatic grades, are compliant with all secure printing techniques and finest choice for inlay applications. White PC films have a thickness range of 30 to 400 µm. Applications include roll or sheet based and produced as matte/matte or velvet/matte upon request.

PROPERTIES		TEST METHOD	UNIT	VALUE
General Properties				
Gloss, 60° Top side		ISO 2813	Digits	≥ 15
Gloss, 60° Reverse side		ISO 2813	Digits	≥ 15
Density (20°C method C)		ISO 1183	g/cm ³	1.36
Mechanical Properties				
Tensile Strength at break	$\frac{MD}{TD}$	ISO 527	MPa	≥50 ≥50
Elongation at break		ISO 527	%	>50
Thermal Properties				
Shrinkage, parallel (130°C 1 h)		DIN 53752	%	<0,5
Shrinkage, across (130°C 1 h)		DIN 53752	%	<0,5
Optical Properties				
Opacity		ISO 13468-2	%	>95
Others				
Surface Tension (Front-Back)		Dyne Pen	Dyne	42-42

- These properties are typical values for 100 µm film; not guaranteed values
- Edition date 11/2020