

## Technical Data Sheet

### ► Typical Property Values

Properties		Test Method	Value	Units
Physical				
Density	Laser 30 / White 50	ASTM D 792	1.3	g/cm³
	Laser 50 / White 80		1.3	g/cm³
	Laser 50 / White 100		1.31	g/cm³
Mechanical				
Tensile Strength		ISO 527	≥ 50	N/mm²
Elongation at break		ISO 527	≥ 50	%
Thermal				
VICAT		ISO 306	148 ± 5	°C
Manufacturing Specifications				
Thickness tolerance		ISO 4593	See table <sup>*1</sup>	
Dimension tolerance		Internal method	<0.5	mm
Flatness/waviness		Internal method	≤ 3	mm
Surface Roughness		*Please see the note below.		

\* Table 1

Thickness range	Tolerance
0.03 ~ 0.10 mm	+/- 5 µm
0.11~0.20 mm	+/- 5 %
0.21 mm ~	+/- 10 µm

**Labeling and REACH applications** This product data sheet is only valid in conjunction with the latest edition of the corresponding Safety Data Sheet. Any updates to safety safety-relevant information – in accordance with statutory requirements – will only be reflected in the Safety Data Sheet, copies of which will be revised and distributed. Information regarding the current classification and labeling, applications, processing methods, and other safety-related data can be found in the currently valid Safety Data Sheet.

Edition date : 2025-02-28

\*For further details or inquiries regarding our products, please feel free to contact us.

EKSİM TEKNOLOJİ VE GÜVENLİK ÇÖZÜMLERİ A.Ş.

[www.exim.com.tr](http://www.exim.com.tr)

Phone: +902123494800 Fax: +902123494801



## Coex (Laser / White)/ Coex AS (Laser AS / White AS)

### Description of the Product

- Reported values based on 100 micron thickness film. The surface structure is one side velvet one side matte.
- The our products have the REACH and ROHS certificates.
- \*For each type of polycarbonate film, we offer a variety of surface options, including glossy, fine matte, matte, velvet finishes

---

\*\*The information in this Technical Data Sheet is believed to be accurate as of its date. However, the use of our products, technical support, and related information (whether communicated verbally, in writing, or through evaluations), including suggested formulations and recommendations, is entirely outside our control. Therefore, it is essential for you to conduct thorough testing to ensure our products meet your specific processing and usage requirements. This evaluation should include assessments of technical suitability, health and safety considerations, environmental impact, and regulatory compliance. Please note that some of the test results may change and Exim has not necessarily conducted such testing for your specific use case, nor have we obtained any formal approvals or licenses for specific applications of the product, unless explicitly stated otherwise.

All information and technical support provided are offered without any warranty or guarantee and may be subject to change without prior notice. By using our products, information, or technical assistance, you accept full responsibility and agree to indemnify and hold Exim harmless from any liability—whether in tort, contract, or otherwise—arising from such use. Any statement or recommendation not explicitly included in this document is not authorized and will not bind Exim.

\*\*This information is intended solely for our customers and relevant competent authorities. It is not meant to be reproduced, whether partially or in full, in printed or electronic formats (e.g., via the internet) by any other parties without prior written permission.

---

Edition date : 2025-02-28

---

EKSİM TEKNOLOJİ VE GÜVENLİK ÇÖZÜMLERİ A.Ş.

[www.exim.com.tr](http://www.exim.com.tr)

Phone: +902123494800 Fax: +902123494801